

In page 2 of 3, Clause - 5 'QUALITY REQUIREMENTS' shall be read as follows instead of existing :

5. **QUALITY REQUIREMENTS** : Quality Requirements shall be as per Table-1 (Chemical Composition), Table-2 (Mechanical Properties) and Clause 2 of C1001 Issue-03.

**TABLE-1**

**DESIGNATION AND GRADES FOR DIFFERENT THICKNESSES OF PLATES**

SL No	THICKNESS mm	GRADES TO BE USED	DESIGNATION
01	5	A	C100101005
02	6	A	C100101006
03	8	A	C100101008
04	10	B	C100101010
05	12	B	C100101012
06	14	B	C100101014
07	16	B	C100101016
08	20	B	C100101020
09	22	B	C100101022
10	25	B	C100101025
11	28	B	C100101028
12	32	B	C100101032
13	36	B	C100101036
14	40	B	C100101040
15	45	B	C100101045
16	50	B	C100101050
17	56	B	C100101056
18	63	B	C100101063
19	70	B	C100101070
20	75	B	C100101075
21	80	B	C100101080
22	85	B	( C100101085 )
23	100	B	C100101100
24	110	B	C100101110
25	130	B	C100101130
26	180	B	C100101180

- Note :** 1) Sizes whose designations are shown in brackets shall not be used in new designs.  
2) Superior grades are acceptable, if offered.

APPROVED BY:

*[Signature]*  
GE

Ref : I) Minutes of PR meeting of Sept. 2011 held at EMD  
II) EP & ETD directives vide ref: EMIR/Steel Plates/GE dt. 2011-09-22



NEW FRONTIERS. NEW DREAMS

# COMPANY STANDARDS

TITLE :

PLATES FOR MEDIUM STRENGTH  
STRUCTURAL PURPOSE

C1001-01

PAGE No. 01 OF 03

DATE: 2008-05-17

## 0. GENERAL INFORMATION :

- This is a branch standard of Company Standard C1001 Issue-03 and is meant for plates.
- The quality requirements of the steel grades shall be as per C1001 Issue-03.
- This Issuance supersedes C1001-01 Issue-02 dated 2002-09-15.

## 1. SCOPE :

This standard provides the recommended sizes and tolerances, supply condition, quality requirements, designation and marking of plates of different thicknesses.

## 2. DEFINITION :

Plate is a hot rolled flat product rolled from ingot or slab; rectangular in cross section, of thickness over 5mm, of width over 1000 mm, and supplied in straight lengths.

## 3. CONDITION OF SUPPLY :

### 3.1 FREEDOM FROM DEFECTS - WELD REPAIRS :

- Material supplied shall be free from mill scale, heavy rust, corrosion pitting, cracks and laminations.
- Minor surface defects may be removed by the manufacturer / supplier by grinding, provided the thickness is not reduced locally by more than 4 % below the minimum specified nominal thickness.
- Weld repair for removal of surface defects is not permissible.
- Non-Destructive tests to be carried out as per Purchase Order/ Contract.
- The plates shall be provided with a corrosion preventive coating to suit transit and storage.

PREPARED BY: CSD/  
CFWC-MATERIALS

ISSUE No. :  
03

REPLACES:

REF :

APPROVED BY :

G

E

DCM



**4. MATERIAL :**

The material shall conform to Company Standard C1001 Issue-03 'Medium Strength Structural Steel'. Steel grades to be used for different plate thicknesses shall be as per Table-1.

**5. QUALITY REQUIREMENTS :**

Shall be as per Table-1 & Table-2 and Clause 2 of C1001 Issue-03.

**TABLE - 1**  
**DESIGNATION AND GRADES FOR DIFFERENT THICKNESSES OF PLATES**

Sl. No.	THICKNESS mm	GRADES TO BE USED IN ORDER OF PREFERENCE *	DESIGNATION
01	5	A	C100101005
02	6	A	C100101006
03	8	A	C100101008
04	10	C	C100101010
05	12	C	C100101012
06	14	C	C100101014
07	16	C	C100101016
08	20	C	C100101020
09	22	C	C100101022
10	25	C	C100101025
11	28	C	C100101028
12	32	C	C100101032
13	36	C / B	C100101036
14	40	C / B	C100101040
15	45	C / B	C100101045
16	50	C / B	C100101050
17	56	C / B	C100101056
18	63	C / B	C100101063
19	70	C	C100101070
20	75	C	C100101075
21	80	C	C100101080
22	85	C	(C100101085)
23	100	C	C100101100
24	110	C	C100101110
25	130	C	C100101130
26	180	C	C100101180

Note : Sizes whose designations are shown in brackets shall not be used in new designs.

\* As per Company Standard C1001 Issue-03 / IS : 2062 latest issuance.

Superior grades are acceptable, if offered, eg. Grade C inplace of grade B and grade B inplace of grade A.

This document is the property of BEML Limited, India. It must not be used directly or indirectly in any way detrimental to the interest of Company without written consent of the proprietors.



COMPANY STANDARDS

C1001-01

TITLE :  
PLATES FOR MEDIUM STRENGTH  
STRUCTURAL PURPOSE

PAGE No. 03 OF 03

DATE: 2008-05-17


6. DESIGNATION :

A plate is designated by 10 – digit code.

The first 5 digits pertain to the material . 6<sup>th</sup> and 7<sup>th</sup> digits signify shape/ Process. The last 3 digits signifies the thickness of plate.

Example :

A 6 mm thick plate shall be designated as C100101006 and a plate of 110 mm thickness shall be designated as C100101110.



7. DIMENSIONS AND TOLERANCES :

Preferred thickness of plates shall be as indicated in Table-1

Width and length of plates shall be as per the Purchase Order / Contract.

Unless otherwise specified, tolerances shall be as per latest issuance of IS : 1852, 'Rolling and cutting tolerances for hot rolled steel products'.

8. COLOUR CODE :

Colour code shall be Grey - Aluminium White - Black. For further details refer to Company Standard PR1002-C.

9. MARKING :

The products shall be suitably marked to identify the following :

- Manufacturer's Name/Trade mark
- Material and Grade
- Size
- Heat number

10. Note : The latest issuance of Standards cited shall be referred.

---oOo---

This document is the property of BEML Limited, Ind. It must not be used directly or indirectly in any way detrimental to the interest of Company without written consent of the proprietors.